



## PRODUCT DATA

# WASH PRIMER

Polyvinyl butyral  
& Phenolic resins

### DESCRIPTION

Two component primer for galvanized surfaces, aluminium, steel e.t.c

---

### RECOMMENDED USE

It has excellent adhesion to galvanized surfaces, aluminium and steel. It prepares the surface for the paint system which will follow.

---

### PHYSICAL DATA

- **Shade:** Ochre
  - **Finish:** Matt
  - **Volume solids:** 11,5 %
  - **Specific gravity:** 0,96 Kg / Lt
  - **Indicated dry film thickness:** Dry film 10 – 20 µm
  - **Theoretical spreading rate:** 5,5 – 11,5 m<sup>2</sup>/Lt
  - **Drying time:**
    - **Dry to touch:** 5-15 min 23° C 50 % Related humidity
    - **Final:** 6-8 hours 23° C 50 % Related humidity
    - **Recoat time:** 8 – 24 hours
- 

### SURFACE PREPARATION

In clean surfaces free from oils, dust e.t.c., we apply a thin coat.

---

### APPLICATION DETAILS

- **Mixing:** We mix the whole quantity of A' component with the whole quantity of B' component.
  - **Ratio :** A' component : B' component 1 : 1
  - **Pot life :** 6 – 8 hours
  - **Dilution:** without dilution.
  - **Tools cleaning:** with solvent N'201.
- 

### SAFETY

The second component of the product contains phosphoric acid, so the user must take care of personal protection. Avoid the contact with skin. Avoid the inhalation of spray. Wear suitable protective gloves and face protection.

The above information and our technical advice-whether verbal or in writing-are given in good faith and according to our tests. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses.