



PRODUCT DATA

OMEGA EXT ANTIRUST PRIMER

Alkyd

DESCRIPTION

Antirust primer based on alkyd resins.

RECOMMENDED USE

For anticorrosive protection of metallic surfaces.

PHYSICAL DATA

- **Shade:** Grey, terra-cotta
 - **Finish:** Matt
 - **Volume solids:** 45 %
 - **Specific gravity:** 1,35 ± 0,05 Kg / Lt
 - **Indicated dry film thickness:** Dry film 40 – 50 µm
 - **Theoretical spreading rate:** 8 – 10 m²/Lt
 - **Drying time:**
 - **Dry to touch:** 1 hour 23° C 50 % Related humidity
 - **Final:** 3 - 4 hours 23° C 50 % Related humidity
-

SURFACE PREPARATION

All the surfaces must be free from rust, oil, dust e.t.c. We recommend sandblasting Sa 2^{1/2}.

APPLICATION DETAILS

- Stir the paint well before its use. The product is applied by spray gun, airless and by brush on smaller surfaces.
 - Dilution: 10 – 25 % with solvent N° 401.
 - Tools cleaning: with solvent N° 401.
-

SAFETY

Use the product to well ventilated place.
Wear suitable protective gloves, eyeglasses and face protection.

The above information and our technical advice-whether verbal or in writing-are given in good faith and according to our tests. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses.