



PRODUCT DATA

ZRP

Alkyd

DESCRIPTION

Zinc rich primer for cold galvanization.

RECOMMENDED USE

It offers cathodic protection to surfaces of steel.

PHYSICAL DATA

- **Shade:** Aluminium grey
 - **Finish:** Matt
 - **Volume solids:** 60 %
 - **Specific gravity:** 2,69 Kg / Lt
 - **Indicated dry film thickness:** Dry film 50 – 80 µm
 - **Theoretical spreading rate:** 7,5 –12 m²/Lt
 - **Drying time:**
 - **Dry to touch:** 15 min 23° C 50 % Related humidity
 - **Final:** 60 min 23° C 50 % Related humidity
-

SURFACE PREPARATION

All the surfaces must be dry and clean before application of the paint. We recommend sandblasting before application.

APPLICATION DETAILS

- Stir the paint well before its use. The product is applied by spray gun, airless and by brush on smaller surfaces.
 - Dilution: 10 – 25 % with solvent N° 401.
 - Tools cleaning: with solvent N°401.
-

SAFETY

Use the product to well ventilated place.
Wear suitable protective gloves, eyeglasses and face protection.

The above information and our technical advice-whether verbal or in writing-are given in good faith and according to our tests. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses.