



PRODUCT DATA

IRON

Alkyd

DESCRIPTION

Alkyd gloss enamel with fast drying mainly for sun protected surfaces.

RECOMMENDED USE

For metallic and wooden surfaces like metallic constructions, agriculture machinery, industrial equipment e.t.c.

PHYSICAL DATA

- **Shade:** Various shades and RAL shades
 - **Finish:** High gloss
 - **Volume solids:** 44 % \pm 1
 - **Specific gravity:** 1,1 \pm 0,2 Kg / Lt
 - **Indicated dry film thickness:** Dry film 30 – 40 μ m
 - **Theoretical spreading rate:** 11 –14 m²/Lt
 - **Drying time:**
 - **Dry to touch:** 2 hours 23° C 50 % Related humidity
 - **Final:** 4 - 6 hours 23° C 50 % Related humidity
-

SURFACE PREPARATION

All the surfaces must be dry and clean before application of the paint. We recommend antirust primer for metallic surfaces.

APPLICATION DETAILS

- Stir the paint well before its use. The product is applied by spray gun, airless and by brush on smaller surfaces.
 - Dilution: 10 – 25 % with solvent N° 401 or N° 402.
 - Tools cleaning: with solvent N° 401 or N° 402.
-

SAFETY

Use the product to well ventilated place.
Wear suitable protective gloves, eyeglasses and face protection.

The above information and our technical advice-whether verbal or in writing-are given in good faith and according to our tests. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses.